Technical Data Sheet

ECOZEN® T90





Product description

ECOZEN® is a glycol-modified polyethylene terephthalate (PETG) with exceptional transparency and chemical resistance. Due to plant-derived biomass components (Carbon-based 2%), ECOZEN® has more heat resistance compared to SKYGREEN® grades. ECOZEN® does not contain Bisphenol derivatives (BPA, etc.) and Phthalate-based plasticizer components regulated by the EU RoHS regulations. It also meets the requirements for food contact materials in Korea, the US, Europe, China, and Japan.

Applications

- Consumer Housewares
- Home Appliances
- Food and Beverage Packaging

Key Attributes

- · High Heat Resistance
- Clarity

Notes

The data listed here is preliminary data sheet of product. Therefore this sheet should not be used to establish specification limits or used alone as a basis for design. This information is not intended as a warranty of any kind. Customers must make their own representative test and assume all risks of use, whether used alone or in combination with other products. SK Chemicals assumes no obligation or liability of any advice furnished by it or results obtained with respect to these products. All warranties of merchantability for a particular purpose or use are excluded and disclaimed.



Typical properties for

ECOZEN® T90



Product Information

Property	Test Method	Unit	Result
Specific Gravity	ASTM D792	-	1.25
Mold Shrinkage	ASTM D955	%	0.2 ~ 0.5
Rockwell Hardness	ASTM D785	R-scale	115
Tensile Strength @ Yield	ASTM D638	Kgf/cm2	480
Tensile Strength @ Break	ASTM D638	Kgf/cm2	490
Elongation @ Yield	ASTM D638	%	5.8
Elongation @ Break	ASTM D638	%	280
Flexural Strength	ASTM D790	Kgf/cm2	720
Flexural Modulus	ASTM D790	Kgf/cm2	20,000
Izod Impact Strength Notched @ 23°C	ASTM D256	J/m	860
Heat Distortion Temperature @ 0.455 MPa / @ 1.820 MPa	ASTM D648	°C	78 / 68
Haze	ASTM D1003	%	< 1.0
Transmittance	ASTM D1003	%	90

The information in this data sheet is, to the best of our knowledge, true and accurate. The representations about the product are based upon test results achieved under laboratory practices supervised and controlled by SK chemicals corporation.

Headquarter / R&D center

310 Pangyo-ro, Bundang-gu, Seongnam-si, Gyeonggi-do, Republic of Korea [13494]

TEL: +82-2-2008-2008 FAX: +82-2-2008-2009

Ulsan Plant

718, Cheoyong-ro, Nam-gu, Ulsan, Republic of Korea [44784]

TEL: +82-52-256-0121 FAX: +82-52-256-0652

Ver.1, '20.08.11



Typical properties for

ECOZEN® T90



Product Information

Test Method	Unit	Result
ASTM D792	-	1.25
ASTM D955	%	0.2 ~ 0.5
ASTM D785	R-scale	115
ISO 527	MPa	45
ISO 527	MPa	54
ISO 527	%	5.3
ISO 527	%	230
ISO 178	MPa	66
ISO 178	MPa	1,790
ISO 180	KJ/m2	93
ISO 75	°C	81 / 68
ASTM D1003	%	< 1.0
ASTM D1003	%	90
	ASTM D792 ASTM D955 ASTM D785 ISO 527 ISO 527 ISO 527 ISO 527 ISO 178 ISO 178 ISO 180 ISO 75 ASTM D1003	ASTM D792 - ASTM D955 % ASTM D785 R-scale ISO 527 MPa ISO 527 MPa ISO 527 % ISO 527 % ISO 527 % ISO 178 MPa ISO 178 MPa

The information in this data sheet is, to the best of our knowledge, true and accurate. The representations about the product are based upon test results achieved under laboratory practices supervised and controlled by SK chemicals corporation.

Headquarter / R&D center

310 Pangyo-ro, Bundang-gu, Seongnam-si, Gyeonggi-do, Republic of Korea [13494]

TEL: +82-2-2008-2008 FAX: +82-2-2008-2009

Ulsan Plant

718, Cheoyong-ro, Nam-gu, Ulsan, Republic of Korea [44784]

TEL: +82-52-256-0121 FAX: +82-52-256-0652

Ver.1, '20.08.11