

Date Prepared: 22th, Dec, 2021

## **Random PP R390Y**

YUPLENE R390Y is random polypropylene that is made for injection molding. It has high impact strength and excellent transparency. Since its excellent flow property makes it suitable for various large size home appliances and thin wall products. It can be used for food packaging, packaging container, and various home appliances. YUPLENE R390Y complies with FDA regulation in 21 CFR 177.1520 and 21 CFR 178.2010 for food packaging substances.

## **Application**

Injection molding / Home appliances, Transparent container

## **Characteristics**

High transparency & Impact strength, High fluidity, Low thickness

## **Physical Properties**

	Value	Unit	Test Method
Melt Index (2.16kg, 230°C)	45	g/10min	ASTM D1238
Tensile Strength at Yield	300	kg/cm <sup>2</sup>	ASTM D638
Elongation at Break	>500	%	ASTM D638
Flexural Modulus	12000	kg/cm <sup>2</sup>	ASTM D790
Izod Impact Strength (Notched, 23°C)	4.0	kg·cm/cm	ASTM D256
Hardness (Rockwell)	95	R Scale	ASTM D785
Softening Point (Vicat)	130	°C	ASTM D1525
Heat Distortion Temperature (0.45Mpa)	80	°C	ASTM D648
Haze (1mm)	6	%	ASTM D1003

<sup>\*</sup> These are typical properties only, and are not to be construed as specific limits.

Head Office 99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea

Tel. 82-2-2121-6483 Fax. 82-2-2121-6909

SK Institute of 140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea Technology Tel. 82-42-609-8370 Fax. 82-42-609-8394

Online www.skgeocentric.com www.skchem.com

ISO 9001 Certified





<sup>\*\*</sup> Processing method: Injection molding