



國喬石油化學股份有限公司
GRAND PACIFIC PETROCHEMICAL CORPORATION

總公司：台北市松山區南京東路四段一號十樓
Head Office: 10FL. No. 1, Nanjing E. Road, Sec. 4, Taipei 105, Taiwan, R.O.C.
TEL: (886)-2-8770-4567 FAX: (886)-2-2545-8755

TYPICAL PROPERTIES OF ABS POWDER 60P

| 名稱 | | |
|--------------------------------------|--|--------------|
| ABS 60R POWDER 60 P | | |
| 項目 | 產品特性 | |
| Typical properties | Test Methods | SPEC |
| Appearance | Visually : colorless powder. | white powder |
| Moisture (wt.%) | Oven(105°C/1Hr) | 1.0 max. |
| Bulk Density (g/100ml) | JIS/ASTM method | 0.33 max. |
| | 1.FT-IR instrument | 61.0 max. |
| Rubber content (wt.%) | 2.Wijs solution method (Rough) | ---- |
| Heat Stability | muffle furnace (180°C /60min.) | Pass |
| Particle Size , Mesh 20 on(min) | ASTM E-11 | 25.0 max. |
| Particle Size , Mesh 200thru (max) | ASTM E-11 | 15.0 max. |
| Processing Temperature | Thermogravimetric analysis , (TGA) | 180~220°C |
| Yellowness Index | ASTM D-1925 | 17-21 |
| Processing Temperature | 180°C — 220°C | |

* 60P 不適於單獨押出使用。

These property values are believed to be representative under the specific test conditions and are not intended to serve as product specifications.